



# Parquet Pro



A waterborne two pack polyurethane lacquer exhibiting excellent light fastness and abrasion resistance, with a high level of resistance to common household liquids. Non flammable with very low odour.

- Extremely durable
- Two component lacquer
- Formulated for heavy traffic applications
- Suitable for sports floors
- Meets BS7044 (Part 4) 1990 for slip resistance

Available as a satin and natural matt finish.

## A tough but natural finish

### Long term performance, ideal for high traffic areas

#### Uses

Designed for application to internal hardwood or softwood floors in domestic and a wide range of commercial uses such as shops, offices, restaurants and public buildings. Suitable for gymnasiums / sports floors.

For other uses, please contact our technical department for advice.

#### Preparation

##### New Floors

The surface to be finished must be clean, dry and free from contamination. Pre-sand using 100 or 120 grit paper and remove sanding dust prior to application.

##### Previously Finished Floors

It is very important to remove all traces of wax or polish and to ensure that the previous coating is sound. Wash with white spirit to remove all traces of wax/polish and sand thoroughly using 100 or 120 grit paper. Ensure the surface is clean and dry and remove all sanding dust. It is recommended that a test area is finished to check the adhesion of the lacquer to the previous coating. Ensure good ventilation if using white spirit to remove old polish.

If in doubt, sand the floor back to bare timber, removing all the old coating then treat as a new floor.

#### Application

Mix 10:1 with Hardener TV1795 prior to use. Allow bubbles to leave lacquer before applying. Use within 4 hours of mixing.

*Then,*

Apply by brush or lambs wool mop applicator.

Light traffic: Apply 2 coats

Normal traffic: Apply 3 coats

Heavy traffic: Apply 4 coats

The lacquer should be lightly abraded between coats using 120 or 150 grit paper.

The lacquer may require thinning with up to 5% water, depending upon application method. Do not use in areas of high humidity or condensation.

#### Drying

Can be re-coated from three hours onwards under normal drying conditions (20°C and 60% RH).

The finished floor will take normal foot traffic after overnight drying but may remain susceptible to marking by furniture, carpets, rugs etc. until fully cured approximately three days after finishing.

Drying times will be extended under conditions of low temperature or high humidity.

#### Other

##### Coverage

8 - 12 sq. metres per litre depending upon the surface and application.

##### Cleaning Equipment

Tools, brushes etc. may be cleaned using water containing a small amount of detergent.

##### Storage

Store away from frost and direct sunlight.

##### Maintenance

Vacuum clean or wipe with a damp cloth or mop. Do not over-wet the floor. If after a period of time, the floor starts to show signs of wear, a further coat of lacquer can be applied after preparation as detailed above. Floors can be polished if desired.

##### Health & Safety

Refer to separate health and safety data sheet.

